

# AC 7450

pebble floor compound

## Description and application

Qeshfloor AC 7450 pebble floor compound is a 1-component, water-based floor finish based on an acrylate dispersion.

Qeshfloor AC 7450 pebble compound is especially suitable for:

- ▶ sealing epoxy-bonded pebble floors.

A pebble floor finished with Qeshfloor AC 7450 pebble floor compound is more easy to clean and maintain.

Important:

- ▶ Not suitable for application in wet rooms/areas!
- ▶ Components from, for example, car and bicycle tyres cause black marks on an acrylate floor finish!

## Important

- ▶ Application conditions:  
 Minimum sub-floor temperature: 10°C and 3°C above the dew-point.  
 Optimum application temperature: 20°C.  
 Maximum relative humidity (R.H.): 85%.
- ▶ Use neutral or slightly alkaline cleaning agents.
- ▶ Qeshfloor cleaning cloths\* from Unipro are particularly suitable for removing wet splashes.
- ▶ For further information consult the 'Guidelines for cleaning Qeshfloor pebble floors'.
- ▶ It is possible to provide you with individual cleaning and maintenance advice.
- ▶ Store exclusively in the original packaging and store in a cool, dry, well-ventilated place.

## Properties / product advantages

- ▶ Transparent
- ▶ Solvent-free
- ▶ Thixotropic

## Technical information

DUST-DRY	after ca. 16 hours**
FOOT TRAFFIC	after ca. 24 hours**
COATING TREATMENTS	after ca. 24 hours**
DENSITY	mixed product ca. 1.02 kg/dm <sup>3</sup>
STORAGE LIFE	under favourable storage conditions ca. 12 months
COLOUR	semi-transparent
APPEARANCE	1 layer: silky gloss, essentially the structure of the pebble floor. 2 layers: smooth, silky gloss structure
MECHANICAL LOADS	after 3 x 24 hours**
CHEMICAL AND WATER LOADS	after 7 x 24 hours**
SOLID CONTENT	ca. 48 wt.%
COVERAGE	0.7 - 1.2 kg/m <sup>2</sup> per layer, depending on the pebbles used for the floor
PACKAGING	10 kg bucket
RESISTANCE TO FROST	no

Qeshfloor Industrial Flooring  
Industriestraat 15  
P.O.box 33  
7480 AA Haaksbergen  
Telefoon (+31) 53 573 73 73  
Fax (+31) 53 573 73 33  
info@unipro.nl  
www.qeshfloor.com

Qeshfloor a brand of Unipro bv

# AC 7450

## Sub-floor

The pebble floor must have been hardened for at least 24 hours. It must also be dry, clean, free of grease and free of substances which can reduce the adhesion.

## Application of Qeshfloor AC 7450\*\*\*

Apply Qeshfloor AC 7450 pebble floor compound to the pebble floor using a plastic board-spreader.

Clean equipment immediately after use with lukewarm water.

## Work safety

Hazard class: none.

### REVISIONNUMBER

AC 7450/01-11-06/rev.:0

Unipro works with a quality assurance system which conforms to the NEN-EN-ISO 9001/14001 standard and which has been certified by TÜV Nederland QA. This means that Unipro's products and services meet the specifications described in this QA system. No liability for any damage that results from the use of the product can be accepted as individual circumstances and working practices are unknown. This information leaflet nullifies earlier documentation sheets. © Unipro B.V. 2006. All rights reserved. No part of this sheet may be reproduced in any form without permission in writing from Unipro B.V.