

# Chemical resistance list

## Qeshfloor EP 1500 repair mortar

Chemical	%	Qeshfloor EP 1500
<b>Inorganic acids</b>		
1. Phosphoric acid	10	X
2. Nitric acid	10	X/X
3. Concentrated nitric acid		-
4. Hydrochloric acid	20	X/X
5. Hydrochloric acid	> 20	-
6. Sulphuric acid	10	X
7. Sulphuric acid	30	X/X
8. Sulphuric acid	> 30	-
<b>Organic acids</b>		
1. Acetic acid	10	X
2. Acetic acid	> 10	-
3. Lactic acid	5	X
4. Formic acid	5	-
<b>Alkalis</b>		
1. Sodium/potassium hydroxide	10	X
2. Sodium/potassium hydroxide	50	X
3. Ammonia	10	X
4. Ammonia	25	X

# Chemical resistance list

## EP 1500

Chemical	%	Qeshfloor EP 1500
<b>Solvents</b>		
1. Petrol		X
2. Turpentine		X
3. Toluene		X
4. Xylene		X
5. Benzene		X
6. N-butanol		X
7. Ethanol	30	X
8. Acetone		-
9. Methylene chloride		-
10. Perchloroethylene		X/X
11. Carbon tetrachloride		X
12. Trichloroethylene		X/X
<b>Oils and greases</b>		
1. Vegetable oil		X
2. Mineral oil		X
3. Diesel oil		X
4. Brake oil		X
5. Silicone oil		X
<b>Miscellaneous</b>		
1. Vegetable and fruit juices		X
2. Beer		X
3. Wine		X
4. Hydrogen peroxide	10	X
5. Salts (general)		X

Duration of the exposure: 7 days at 20°C

REVISIONNUMBER  
EP 1500/01-11-06/rev.:1

Unipro works with a quality assurance system which conforms to the NEN-EN-ISO 9001/14001 standard and which has been certified by TÜV Nederland QA. This means that Unipro's products and services meet the specifications described in this QA system. No liability for any damage that results from the use of the product can be accepted as individual circumstances and working practices are unknown. This information leaflet nullifies earlier documentation sheets. © Unipro B.V. 2006. All rights reserved. No part of this sheet may be reproduced in any form without permission in writing from Unipro B.V.