

# Chemical resistance list

## Qeshfloor EP 3900 OV floor coating

Chemical	%	Qeshfloor EP 3900 OV
<b>Inorganic acids</b>		
1. Phosphoric acid	10	X
2. Nitric acid	10	X/X
3. Concentrated nitric acid		-
4. Hydrochloric acid	20	X
5. Hydrochloric acid	> 20	-
6. Sulphuric acid	10	X
7. Sulphuric acid	30	X/X
8. Sulphuric acid	> 30	-
<b>Organic acids</b>		
1. Acetic acid	10	-
2. Acetic acid	> 10	-
3. Lactic acid	5	-
4. Formic acid	5	-
<b>Alkalis</b>		
1. Sodium/potassium hydroxide	10	X
2. Sodium/potassium hydroxide	50	X
3. Ammonia	10	X
4. Ammonia	25	X

# Chemical resistance list

## EP 3900 OV

Chemical	%	Qeshfloor EP 3900 OV
<b>Solvents</b>		
1. Petrol		X
2. Turpentine		X
3. Toluene		X
4. Xylene		X
5. Benzene		X
6. N-butanol		X
7. Ethanol	30	X
8. Acetone		-
9. Methylene chloride		-
10. Perchloroethylene		X
11. Carbon tetrachloride		X
12. Trichloroethylene		X
<b>Oils and greases</b>		
1. Vegetable oil		X
2. Mineral oil		X
3. Diesel oil		X
4. Brake oil		X
5. Silicone oil		X
<b>Miscellaneous</b>		
1. Vegetable and fruit juices		X
2. Beer		X
3. Wine		X
4. Hydrogen peroxide	10	X
5. Salts (general)		X