

# Guidelines for applying

## Qeshfloor EP 6200 screed

	Description	Tools/Equipment
<b>Temperature and relative humidity (R.H.)</b>	<ul style="list-style-type: none"> <li>▶ Minimum temperature in the working area: 15°C.</li> <li>▶ Minimum floor temperature: 10°C and 3°C above the dew-point to prevent condensation.</li> <li>▶ R.H.: maximum 85%</li> <li>▶ Maximum ambient temperature: 35°C.</li> <li>▶ High temperatures shorten the application time.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Temperature measuring device</li> <li>▶ Hygrometer</li> <li>▶ Floor temperature measuring device</li> <li>▶ Dew-point table</li> </ul>
<b>Safety measures</b>	<ul style="list-style-type: none"> <li>▶ As indicated on the product label.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Protective wear</li> </ul>
<b>Sub-floor</b>	<ul style="list-style-type: none"> <li>▶ Jet-clean cement and anhydrite bonded sub-floors.</li> <li>▶ Remove any extraneous material by sanding or blasting.</li> <li>▶ Fill small holes and seams with a suitable putty.</li> <li>▶ For larger repairs use Qeshfloor EP 1500 repair mortar* or UZIN NC 182 filler and levelling compound*.</li> <li>▶ Vacuum the sub-floor using an industrial vacuum.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Industrial vacuum</li> <li>▶ Blasting machine</li> <li>▶ Sanding machine</li> <li>▶ Putty knife</li> <li>▶ Flat trowel</li> </ul>
<b>Mixing the screed</b>	<ul style="list-style-type: none"> <li>▶ Stir component A.</li> <li>▶ Pour component B into component A.</li> <li>▶ Scrape the container out well to ensure all material is transferred.</li> <li>▶ Mix using a drill with a mixer attachment that extends to the base of the container.</li> <li>▶ Mix until the mixture is homogeneous.</li> <li>▶ Mixing time: at least 3 minutes.</li> <li>▶ In order to prevent unmixed material being used from the base/edges of the mixing vessel, transfer the mixture to a clean vessel and then mix again.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Drill with mixer attachment</li> <li>▶ Clean working vessel</li> </ul>
<b>Application of the screed</b>	<ul style="list-style-type: none"> <li>▶ Pour the mixed material onto the sub-floor (do not scrape out) and distribute with a flat trowel / knife or rubber wiper (not too flexible).</li> </ul>	<ul style="list-style-type: none"> <li>▶ Flat trowel</li> <li>▶ Knife</li> <li>▶ Rubber wiper</li> </ul>
<b>Hardening time at 20°C and 65% R.H.</b>	<ul style="list-style-type: none"> <li>▶ Suitable for foot traffic and further treatments after ca. 16 hours.</li> <li>▶ Apply the next layer within 24 hours. Thereafter the screed must first be roughened.</li> <li>▶ Low temperatures retard the hardening process.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Sanding machine</li> </ul>
<b>Cleaning tools/equipment</b>	<ul style="list-style-type: none"> <li>▶ Clean tools/equipment immediately after use with UZIN VE 124 cleaner*.</li> </ul>	

Qeshfloor Industrial Flooring  
Industriestraat 15  
P.O.box 33  
7480 AA Haaksbergen  
Telefoon (+31) 53 573 73 73  
Fax (+31) 53 573 73 33  
info@unipro.nl  
www.qeshfloor.com

Qeshfloor a brand of Unipro bv

REVISIONNUMBER  
guidelines EP 6200/01-11-06/rev.:0

Unipro works with a quality assurance system which conforms to the NEN-EN-ISO 9001/14001 standard and which has been certified by TÜV Nederland QA. This means that Unipro's products and services meet the specifications described in this QA system. No liability for any damage that results from the use of the product can be accepted as individual circumstances and working practices are unknown. This information leaflet nullifies earlier documentation sheets. © Unipro B.V. 2006. All rights reserved. No part of this sheet may be reproduced in any form without permission in writing from Unipro B.V.