

# Guidelines for applying

## Qeshfloor EP 6550 multiprimer

Description	Tools/Equipment
<b>Temperature and atmospheric Relative Humidity (R.H.)</b> <ul style="list-style-type: none"> <li>▶ Minimum temperature in the working area: 15°C.</li> <li>▶ Minimum floor temperature: 10°C and 3°C above the dew-point to prevent condensation.</li> <li>▶ Atmospheric R.H.: maximum 85%</li> <li>▶ Maximum ambient temperature: 35°C.</li> <li>▶ High temperatures shorten the application time.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Temperature measuring device</li> <li>▶ Hygrometer</li> <li>▶ Floor temperature measuring device</li> <li>▶ Dew-point table</li> </ul>
<b>Safety measures</b> <ul style="list-style-type: none"> <li>▶ As indicated on the product label.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Protective wear</li> </ul>
<b>Sub-floor</b> <ul style="list-style-type: none"> <li>▶ Remove any extraneous material by sanding or blasting.</li> <li>▶ Fill small holes and seams with a suitable putty.</li> <li>▶ For larger repairs use Qeshfloor EP 1500 repair mortar* or UZIN NC 182 filler and levelling compound*.</li> <li>▶ Vacuum the sub-floor using an industrial vacuum cleaner.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Industrial vacuum cleaner</li> <li>▶ Blasting machine</li> <li>▶ Sanding machine</li> <li>▶ Putty knife</li> <li>▶ Flat trowel</li> </ul>
<b>Mixing the primer</b> <ul style="list-style-type: none"> <li>▶ Pierce the base of the top container, so allowing component B to flow into component A.</li> <li>▶ Ensure all material is transferred.</li> <li>▶ Remove the top from the can.</li> <li>▶ Then mix using a drill with a mixer attachment until the mixture is homogeneous.</li> <li>▶ Mixing time: at least 2 minutes.</li> <li>▶ In order to prevent unmixed material being used from the base/edges of the mixing vessel, transfer the mixture to a clean vessel and then mix again.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Drill with mixer attachment</li> <li>▶ Clean working vessel</li> </ul>
<b>Application of the primer</b> <ul style="list-style-type: none"> <li>▶ Apply along the edges with a brush.</li> <li>▶ Apply a thin layer to the remaining surface using a 25 cm wide lamb's fleece roller or polyester roller or distribute with a flat trowel / knife or rubber wiper (not too flexible).</li> <li>▶ Distribute the primer so that the sub-floor is totally covered.</li> <li>▶ Apply as thinly as possible.</li> <li>▶ To improve the surface, apply a thicker layer.</li> </ul>	<ul style="list-style-type: none"> <li>▶ Brush</li> <li>▶ 25 cm lamb's fleece or polyester roller</li> <li>▶ Flat trowel</li> <li>▶ Knife</li> <li>▶ Wiper</li> </ul>
<b>Broadcast the primer with sand</b> <ul style="list-style-type: none"> <li>▶ When using as an adhesion layer under mortar, pebble and cast floors, sand in the wet primer with Qeshfloor sand (grain size: 0.1 – 0.3 mm).</li> <li>▶ Remove excess sand after the indicated hardening time.</li> <li>▶ If the primer is used under a cement based levelling layer, this must be 'fully' broadcast with Qeshfloor sand (grain size: 0.1 – 0.3 mm).</li> </ul>	<ul style="list-style-type: none"> <li>▶ Spiked shoes</li> <li>▶ Sweeping brush</li> </ul>
<b>Hardening time at 20°C and 65% atmospheric R.H.</b> <ul style="list-style-type: none"> <li>▶ Suitable for foot traffic and further treatments after ca. 16 hours.</li> <li>▶ Low temperatures retard the hardening process.</li> </ul>	
<b>Cleaning tools/ equipment</b> <ul style="list-style-type: none"> <li>▶ Clean tools/equipment immediately after use with UZIN VE 124 cleaner*.</li> </ul>	

Qeshfloor Industrial Flooring  
Industriestraat 15  
P.O.box 33  
7480 AA Haaksbergen  
Telefoon (+31) 53 573 73 73  
Fax (+31) 53 573 73 33  
info@unipro.nl  
www.qeshfloor.com

Qeshfloor a brand of Unipro bv

REVISIONNUMBER  
guidelines EP 6550/01-11-06/rev.:0

Unipro works with a quality assurance system which conforms to the NEN-EN-ISO 9001/14001 standard and which has been certified by TÜV Nederland QA. This means that Unipro's products and services meet the specifications described in this QA system. No liability for any damage that results from the use of the product can be accepted as individual circumstances and working practices are unknown. This information leaflet nullifies earlier documentation sheets. © Unipro B.V. 2006. All rights reserved. No part of this sheet may be reproduced in any form without permission in writing from Unipro B.V.