

Chemical resistance list

Qeshfloor PU 7770 matt sealant layer

Chemical	%	Qeshfloor PU 7770
Inorganic acids		
1. Phosphoric acid	10	-
2. Nitric acid	1	-
3. Hydrochloric acid	20	-
4. Hydrochloric acid	> 20	-
5. Sulphuric acid	20	-
Organic acids		
1. Acetic acid	10	-
2. Acetic acid	> 10	-
3. Lactic acid	3	-
4. Formic acid	5	-
Alkalis		
1. Sodium/potassium hydroxide	20	X/X
2. Sodium/potassium hydroxide	50	-
3. Ammonia	20-25	-
4. Ammonia	32	-
Solvents		
1. Petrol		-
2. Toluene		-
3. Xylene		-
4. Benzene		-
5. N-butanol		-
6. Ethanol	30	X/X
7. Acetone		-
8. Methylene chloride		-

Chemical resistance list

PU 7770

Chemical	%	Qeshfloor PU 7770
Oils and greases		
1. Diesel oil		X
2. Brake oil		-
Miscellaneous		
1. Vegetable and fruit juices		-
2. Beer		X
3. Wine		X
4. Hydrogen peroxide	10	-
5. Salts (general)		X

The chemical resistance applies for a closed layer of coating of at least 0.1 mm thickness.

Duration of the exposure: 7 days at 20°C

REVISIONNUMBER

PU 7770/01-11-06/rev.:0

Unipro works with a quality assurance system which conforms to the NEN-EN-ISO 9001/14001 standard and which has been certified by TÜV Nederland QA. This means that Unipro's products and services meet the specifications described in this QA system. No liability for any damage that results from the use of the product can be accepted as individual circumstances and working practices are unknown. This information leaflet nullifies earlier documentation sheets. © Unipro B.V. 2006. All rights reserved. No part of this sheet may be reproduced in any form without permission in writing from Unipro B.V.